

**RESULTS****DETERMINATION OF BREAKING STRENGTH AND ELONGATION**

Standard: UNE 40085

Apparatus: INSTRON Dynamometer

Number of specimens: Five for each direction

<u>Reference</u>	<u>Direction</u>	<u>Average breaking strength (N)</u>	<u>CV(%)</u>	<u>Average Elongation (%)</u>	<u>CV(%)</u>
TEJIDO BALI	Warp	1405.00	1.57	63.81	6.42
	Weft	1417.00	2.14	63.71	3.67
TEJIDO DAMA	Warp	1207.00	1.83	32.39	2.03
	Weft	788.90	3.11	15.48	2.38