

RESULTS**DETERMINATION OF TEAR RESISTANCE**

Standard: UNE 40404

Apparatus: Instron Dynamometer

<u>Reference</u>	<u>Tear</u>	<u>Average value (N)</u>	<u>C.V (%)</u>
TEJIDO BALI	Warp	19.96	2.08
	Weft	20.44	6.08
TEJIDO DAMA	Warp	*	*
	Weft	7.09	5.78

REMARK:

Has not been able to determine the tear resistance in warp of the sample "TEJIDO DAMA" all specimens break in the direction of the weft.