

## RESULTS

### DETERMINATION OF THE ABRASION RESISTANCE OF FABRICS

Standard: BS 5690:1991 modified according BS 2543:1995

Apparatus: Martindale Abrasion Tester

Testing Conditions: Rubbing against SM-25 abradant fabric

Testing Pressure: 12 kPa

End Point: 3 yarns broken

Reference: TEJIDO BALI

<u>Test specimen</u>	<u>Change Aspect to end to test</u>	<u>Cycles up to end point</u>
1	3	> 40000
2	3	> 40000
3	3	> 40000
4	3	> 40000
Average value	3	> 40000

**REMARK:**

The displayed table gathers the relative interpretation of the meaning of the degradation of colour valued with a the grey scale:

#### VALORATION OF ESCALE OF GREYS

5	- GOOD
4-3	- FAIR BEHAVIOUR
2-1	- POOR BEHAVIOUR