

RESULTS

DETERMINATION OF THE ABRASION RESISTANCE OF FABRICS

Standard: BS 5690:1991 modified according BS 2543:1995

Apparatus: Martindale Abrasion Tester

Testing Conditions: Rubbing against SM-25 abradant fabric

Testing Pressure: 12 kPa

End Point: 3 yarns broken

Reference: TEJIDO DAMA

<u>Test specimen</u>	<u>Cycles up to change of aspect</u>	<u>Cycles up to end point</u>
1	6000	> 40000
2	6000	> 40000
3	6000	> 40000
4	6000	> 40000
Average value	6000	> 40000

REMARK:

The aspect change has been considered at the moment that is observed on the test tube a partial loss of the hair of the thread of chenille.

The total losses of the hair of the thread of chenille is observed the 10000 cycles.