

RESULTS

COLOUR FASTNESS TO DOMESTIC AND COMMERCIAL LAUNDERING

Standard UNE-EN ISO 105-C06

Apparatus: Linitest

Test number: A1M

Temperature: 40°C

Steel balls: 10

Detergent: ECE reference detergent without optical or chemical brightener

Test piece drying in forced-air circulation dryer

REFERENCE	CHANGE IN COLOUR	STAINING					
		Wool	Acrylic	Polyester	Polyamide	Cotton	Acetate
TEJIDO BALI	5	5	5	5	5	5	5