

## RESULTS

### COLOUR FASTNESS TO DOMESTIC AND COMMERCIAL LAUNDERING

Standard UNE-EN ISO 105-C06

Apparatus: Linitest

Test number: A1M

Temperature: 40°C

Steel balls: 10

Detergent: ECE reference detergent without optical or chemical brightener

Test piece drying in forced-air circulation dryer

<u>REFERENCE</u>	<u>CHANGE IN COLOUR</u>	<u>STAINING</u>	
		<u>Cotton</u>	<u>Polyester</u>
TEJIDO DAMA	5	5	5